


CP4205/TA468/ TA7955



Labels for Life.



Face Stock: 10 mil transparent polycarbonate, one-side matte, one-side polished. This material offers excellent resistance to extreme temperatures and is specifically designed not to shrink. The material also offers great printability without pre-treatment, which allows for multi-layer printing.

Adhesive: 5.2 mil high-performance pressure-sensitive acrylic adhesive, specifically designed for optimal adhesion and clarity. It is designed to offer consistent performance even after exposure to humidity and hot/cold cycles.

Release Liner: 4.2 mil 58# polycoated kraft liner.

- TA468 - single lined
- TA7955 - double lined

Matte Polycarbonate Film

CP4205/TA468/TA7955 is specifically designed to be a screen-printable polycarbonate construction. Key features include: UV-ink printable, transparent, high temperature and abrasion resistance, and high tensile and shear strength. It will meet the most demanding durable labeling requirements.

Typical Applications

- Overlays
- Floor graphics
- Harsh-abrasion environments
- In-mould decoration

Typical Industry Sectors

- Automotive
- Electronics
- Industrial




www.identco.com


CP4205/TA468/TA7955

Matte Polycarbonate Film




Labels for Life.

 **Agency Recognitions**
UL-PGDQ2-MH16225


 **Adhesion**


Stainless steel	118 oz/in	1298 N/m	Acrylic	67oz/in	737 N/m
Acrylic	68 oz/in	748 N/m	Aluminum	115 oz/in	1265 N/m


 **Material Caliper**


Face Stock	.0100"	254.00μ	Liner(kraft 58#)	.0042"	106.68μ
Adhesive	.0052"	132.08μ	Total Material	.0194"	492.76μ

 **Exterior Durability**
Testing is recommended in actual application

 **Temperature Range**
Service Temperature: -40°F to 212°F (-40°C to 100°C)
Minimum Application Temperature: 50°F (-10°C)
Brittleness Temperature: -211°F (-135°C)

 **Shelf Life**
Recommended Storage: 45-90°F (7-32°C) 20-75% R.H.
Shelf Life: 2 years @ recommended storage

 **Recommended Printing**
UV and infrared drying inks

 **Process Durability**
It is recommended that customers test the material in actual application to determine if the material meets all requirements.

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by IDENTCO customers for designs and specifications, or be relied on as meeting specific performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact IDENTCO for further information. Revised 6/23/2017.

UNITED STATES HEADQUARTERS

28164 W. Concrete Drive
Ingleside, IL 60041
Phone: +1 (815) 385 - 0011
Fax +1 (815) 385 - 0359

MEXICO MONTERREY

Carr. a Laredo Km. 16.5 Interior
14B, Col. Moisés Sáenz, 66613
Apodaca, Nuevo Leon
Phone: +52 (81) 8008 - 0438

GERMANY FRANKFURT

Güterbahnhofstrasse 3-7
63450 Hanau
Phone: +49 (6181) 440 830 - 0
Fax: +49 (6181) 440 830 - 99

PRC HONG KONG

Unit 1708, 17/F, 9 Wing Hong St.
Cheung Sha Wan, Kowloon
Phone: +852 2959 2156
Fax: +852 2959 2019

MALAYSIA PENANG

Suite 163E, Level 16, Room 1602
Hunza Tower Gurney Paragon
Jalan Kelawei, Georgetown
10250 Penang
Phone: +6012 466 - 0866