


CP4002



Labels for Life.

Face Stock: 10 mil transparent one side velvet, one side matte polycarbonate film. The material offers excellent resistance to extreme temperatures and is specifically designed to not shrink. The material offers great printability without pre-treatment which allows for multi-layer printing. CP4002 is designed to accept UV ink printing. This material allows for various adhesives to be applied if required by the user.



Transparent Polycarbonate Film

CP4002 is specifically designed to be a screen printable polycarbonate film. Key features include: UV ink printable, roll form availability, transparent, high temperature and harsh abrasion resistance, one side velvet, one side matte and high tensile strength. When used in combination with the recommended IDENTCO adhesives and inks, it will meet the most demanding durable labeling applications.

Typical Applications

- Overlays
- Floor graphics
- Harsh abrasion environment
- In-mould decorations

Typical Industry Sectors

- Automotive
- Electronics
- Industrial



www.identco.com

CP4002

Transparent Polycarbonate Film



Labels for Life.

	Recognitions/Compliance RoHS Directive Compliant 2002/95/EC	
	Material Properties Tensile Strength Elongation at break 100-156%	At yield 8500 psi Ultimate 9000 psi Tensile Modulus 300000 psi
	Material Caliper Face Stock Total Material	.0010" 254.0μ .0010" 254.0μ
	Exterior Durability Testing is recommended in actual application.	
	Temperature Range Heat deflection temperature 290°F (143°C) Shrinkage temperature 302°F (150°C) Brittleness temperature -211°F (135°C)	
	Shelf Life Recommended Storage: 45-90°F (7-32°C) 20-75% R.H. Shelf Life: 2 years @ recommended storage	
	Recommended Inks Screen printed with: Solvent based inks	Water based inks UV & infrared drying inks
	Process Durability It is recommended that customers test this material in actual application to determine if the material meets all requirements.	

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by IDENTCO customers for designs and specifications, or be relied on as meeting specific performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact IDENTCO for further information. Revised 7/11/2017.

UNITED STATES HEADQUARTERS

28164 W. Concrete Drive
Ingleside, IL 60041
Phone: +1 (815) 385 - 0011
Fax +1 (815) 385 - 0359

MEXICO MONTERREY

Carr. a Laredo Km. 16.5 Interior
14B, Col. Moisés Sáenz, 66613
Apodaca, Nuevo Leon
Phone: +52 (81) 8008 - 0438

GERMANY FRANKFURT

Güterbahnhofstrasse 3-7
63450 Hanau
Phone: +49 (6181) 440 830 - 0
Fax: +49 (6181) 440 830 - 99

PRC HONG KONG

Unit 1708, 17/F, 9 Wing Hong St.
Cheung Sha Wan, Kowloon
Phone: +852 2959 2156
Fax: +852 2959 2019

MALAYSIA PENANG

Suite 163E, Level 16, Room 1602
Hunza Tower Gurney Paragon
Jalan Kelawei, Georgetown
10250 Penang
Phone: +6012 466 - 0866